PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

READYMIX CONCRETE

CONCRETE CLASS	**: K – 250**
BATCHING PLANT	**: PT REMICON WIDYAPRIMA**
CONTRACTOR	**: PT WILSON SUKSES MANDIRI**
PROJECT	**: PEMBANGUNAN SEKOLAH SMK N 11**
CODE	**:**
CUBE SIZE	**: 15 x 15 x 15 Cm**
LOCATION	**: Dapur 12 - Batam**
SAMPLE BY	**: QC**

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	22-11-25	29-11-25	7	120±20	8121	426.0	193.06

AVERAGE : 193.06 kg/cm2

~ PERCENTAGE AVERAGE : 77.23%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	**(** **)**	**(** **)**
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

READYMIX CONCRETE

CONCRETE CLASS	**: K – 250**
BATCHING PLANT	**: PT REMICON WIDYAPRIMA**
CONTRACTOR	**: PT WILSON SUKSES MANDIRI**
PROJECT	**: PEMBANGUNAN SEKOLAH SMK N 11**
CODE	**:**
CUBE SIZE	**: 15 x 15 x 15 Cm**
LOCATION	**: Dapur 12 - Batam**
SAMPLE BY	**: QC**

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	22-11-25	6-12-25	14	120±20	8119	537.6	243.64

AVERAGE : 243.64 kg/cm2

~ PERCENTAGE AVERAGE : 97.46%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	**(** **)**	**(** **)**
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

READYMIX CONCRETE

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

CONCRETE CLASS	: K – 250
BATCHING PLANT	: PT REMICON WIDYAPRIMA
CONTRACTOR	: PT WILSON SUKSES MANDIRI
PROJECT	: PEMBANGUNAN SEKOLAH SMK N 11
CODE	:
CUBE SIZE	: 15 x 15 x 15 Cm
LOCATION	: Dapur 12 - Batam
SAMPLE BY	: QC

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	22-11-25	20-12-25	28	120±20	8127	580.4	263.04

AVERAGE : 263.04 kg/cm2

~ PERCENTAGE AVERAGE : 105.21%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	( )	( )
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

READYMIX CONCRETE

CONCRETE CLASS	**: K – 250 PM**
BATCHING PLANT	**: PT REMICON WIDYAPRIMA**
CONTRACTOR	**: PT WILSON SUKSES MANDIRI**
PROJECT	**: PEMBANGUNAN SEKOLAH SMK N 11**
CODE	**:**
CUBE SIZE	**: 15 x 15 x 15 Cm**
LOCATION	**: Dapur 12 - Batam**
SAMPLE BY	**: QC**

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	03-12-25	10-12-25	7	120±20	8133	420.6	190.62

AVERAGE : 190.62 kg/cm2

~ PERCENTAGE AVERAGE : 76.25%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	**(** **)**	**(** **)**
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

READYMIX CONCRETE

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

CONCRETE CLASS	: K – 250 PM
BATCHING PLANT	: PT REMICON WIDYAPRIMA
CONTRACTOR	: PT WILSON SUKSES MANDIRI
PROJECT	: PEMBANGUNAN SEKOLAH SMK N 11
CODE	:
CUBE SIZE	: 15 x 15 x 15 Cm
LOCATION	: Dapur 12 - Batam
SAMPLE BY	: QC

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	03-12-25	17-12-25	14	120±20	8069	541.0	245.18

AVERAGE : 245.18 kg/cm2

~ PERCENTAGE AVERAGE : 98.07%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	( )	( )
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

READYMIX CONCRETE

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

CONCRETE CLASS	: K – 250 PM
BATCHING PLANT	: PT REMICON WIDYAPRIMA
CONTRACTOR	: PT WILSON SUKSES MANDIRI
PROJECT	: PEMBANGUNAN SEKOLAH SMK N 11
CODE	:
CUBE SIZE	: 15 x 15 x 15 Cm
LOCATION	: Dapur 12 - Batam
SAMPLE BY	: QC

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	03-12-25	31-12-25	28	120±20	8110	586.1	265.62

AVERAGE : 265.62 kg/cm2

~ PERCENTAGE AVERAGE : 106.25%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	( )	( )
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

READYMIX CONCRETE

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

CONCRETE CLASS	: K – 250
BATCHING PLANT	: PT REMICON WIDYAPRIMA
CONTRACTOR	: PT WILSON SUKSES MANDIRI
PROJECT	: PEMBANGUNAN SEKOLAH SMK N 11
CODE	:
CUBE SIZE	: 15 x 15 x 15 Cm
LOCATION	: Dapur 12 - Batam
SAMPLE BY	: QC

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	18-12-25	25-12-25	7	120±20	8114	422.0	191.25

AVERAGE : 191.25 kg/cm2

~ PERCENTAGE AVERAGE : 76.50%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	( )	( )
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

READYMIX CONCRETE

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

CONCRETE CLASS	: K – 250
BATCHING PLANT	: PT REMICON WIDYAPRIMA
CONTRACTOR	: PT WILSON SUKSES MANDIRI
PROJECT	: PEMBANGUNAN SEKOLAH SMK N 11
CODE	:
CUBE SIZE	: 15 x 15 x 15 Cm
LOCATION	: Dapur 12 - Batam
SAMPLE BY	: QC

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	18-12-25	1-01-26	14	120±20	8129	541.7	245.50

AVERAGE : 245.50 kg/cm2

~ PERCENTAGE AVERAGE : 98.20%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	( )	( )
Head Laboratory	***Production Manager***		

PT.REMICON Widyaprima

BJS Group

TELP : 459088, 458088, 424888 FAX : 459002, 457088

BJS BUILDING JL.MAJAPAHIT KAV.II BATU AMPAR - PULAU BATAM

READYMIX CONCRETE

CONCRETE CLASS	**: K – 250**
BATCHING PLANT	**: PT REMICON WIDYAPRIMA**
CONTRACTOR	**: PT WILSON SUKSES MANDIRI**
PROJECT	**: PEMBANGUNAN SEKOLAH SMK N 11**
CODE	**:**
CUBE SIZE	**: 15 x 15 x 15 Cm**
LOCATION	**: Dapur 12 - Batam**
SAMPLE BY	**: QC**

"COMPRESSIVE STRENGTH TEST REPORT"

NO SAMPLE	DATE CAST	DATE TEST	AGE (day)	SLUMP (mm)	WEIGHT (gram)	MAXLOAD (kn)	STRENGTH (kg/cm2)
1	18-12-25	15-01-26	28	120±20	8077	573.5	259.91

AVERAGE : 259.91 kg/cm2

~ PERCENTAGE AVERAGE : 103.96%

Ditest Oleh :	Dicheck Oleh :	Dicheck Oleh :	Diketahui Oleh :
PT. Remicon Widyaprima	PT. Remicon Widyaprima	CV. Wilson Sukses Mandiri	

PT. REMICON WIDYAPRIMA
LABORATORY OF CONCRETE

Choerur	**Christanto**	**(** **)**	**(** **)**
Head Laboratory	***Production Manager***		